

Properties of cable with standard Enhanced SM fibre

ESMF, low water peak single mode fibre G652D, OS2

General and application

The optical fibres are made of a high grade doped silica core surrounded by a silica cladding.

They are coated with a dual layer, UV cured acrylate based coating.

This enhanced single mode fibre provides improved performance across the entire 1260 nm to 1625 nm wavelength spectrum due to its low attenuation in 1383 nm, the water-peak region.

Standards and Norms

IEC / EN 60793-2-50 Category B.1.3	EN 50 173-1: cat. OS2 and OS1
ITU-T Recommendation G.652.D and C, B, A	ISO / IEC 11801: cat. OS2 and OS1
IEEE 802.3	ISO / IEC 24702: cat. OS2 and OS1

Optical properties

Attribute	Measurement method	Units	Limits
Mode field diameter at 1310 nm	IEC/EN 60793-1-45	µm	9.0 ± 0.4
Mode field diameter at 1550 nm		µm	10.1 ± 0.5
Chromatic dispersion coefficient:	IEC/EN 60793-1-42		
In the interval 1285 nm – 1330 nm		ps/km • nm	≤ 3
At 1550 nm		ps/km • nm	≤ 18.0
At 1625 nm		ps/km • nm	≤ 22.0
Zero dispersion wavelength, λ ₀		nm	1300 - 1322
Zero dispersion slope		ps/(nm ² • km)	≤ 0.092
Cut-off wavelength	IEC/EN 60793-1-44	λ _{cc} nm	≤ 1260 *
Polarisation mode dispersion (PMD) coefficient	IEC/EN 60793-1-48	ps/√km	≤ 0.5
PMD ₀ Link Design Value (computed with Q=0.01%, N=20)	IEC/EN 60794-3	ps/√km	≤ 0.20

* guaranteed value according to the ITU-T (ATM G650) method

Attenuation

Attribute	Measurement method	Units	Limits
Maximum attenuation value of cable in the interval 1310 nm – 1625 nm	IEC/EN 60793-1-40	dB/km	≤ 0.39
Maximum attenuation value of cable at 1550 nm	IEC/EN 60793-1-40	dB/km	≤ 0.25
Local discontinuity at 1310 and 1550 nm	IEC/EN 60793-1-40	dB	Max. 0.1

Attenuation variation vs Bending

Attribute	Measurement method	Units	Limits
100 turns on a R=25 mm mandrel at 1310 & 1550 nm	IEC/EN 60793-1-47	dB	≤ 0.05
100 turns on a R=30 mm mandrel at 1625 nm	IEC/EN 60793-1-47	dB	≤ 0.05

Group index of refraction

Attribute	Measurement method	Units	Values
1310 nm	IEC/EN 60793-1-22	-	1.467
1550 nm	IEC/EN 60793-1-22	-	1.468
1625 nm	IEC/EN 60793-1-22	-	1.468

Rayleigh Backscatter coefficient (1ns pulse width)

Attribute	Measurement method	Units	Values
1310 nm	-	dB	-79.4
1550 nm	-	dB	-81.7
1625 nm	-	dB	-82.5

Geometrical properties

Attribute	Measurement method	Units	Limits
Cladding diameter	IEC/EN 60793-1-20	µm	125.0 ± 0.7
Cladding non-circularity	IEC/EN 60793-1-20	%	≤ 0.7
Core (MDF) -cladding concentricity error	IEC/EN 60793-1-20	µm	≤ 0.5
Primary coating diameter – ColorLock ^{®XS} and natural	IEC/EN 60793-1-21	µm	242 ± 7
Primary coating non-circularity	IEC/EN 60793-1-21	%	≤ 5
Primary coating-cladding concentricity error	IEC/EN 60793-1-21	µm	≤ 12

Mechanical properties

Attribute	Measurement method	Units	Limits
Proof stress level	IEC/EN 60793-1-30	GPa	≥ 0.7 (≈ 1 %)
Strip force (peak)	IEC/EN 60793-1-32	N	1.2 ≤ F _{peak,strip} ≤ 8.9
Dynamic fatigue resistance aged and unaged	IEC / EN 60793-1-33	(N _d)	≥ 20
Static fatigue, aged	IEC / EN 60793-1-33	(N _s)	≥ 23

All measurements in accordance with ITU-T G650 recommendations

© PrysmianGroup 2017, All Rights Reserved

All sizes and values without tolerances are reference values. Specifications are for product as supplied by PrysmianGroup: any modification or alteration afterwards of product may give different result.

The information contained within this document must not be copied, reprinted or reproduced in any form, either wholly or in part, without the written consent of PrysmianGroup. The information is believed to be correct at the time of issue. PrysmianGroup reserves the right to amend this specification without prior notice. This specification is not contractually valid unless specifically authorised by PrysmianGroup.